



The Chemical Company

CEMENTIUM™ 5350 AE (Formerly known as Cementium 250AE)

High Performance Cement Additive to Increase Air Content in Masonry Cement

DESCRIPTION

CEMENTIUM 5350 AE is an aqueous solution of anionic and non-ionic surfactants.

CEMENTIUM 5350 AE is specially formulated to provide superior workability and placeability of the Masonry cement.

CEMENTIUM 5350 AE is compatible with all types of cement. It complies with ASTM C465-99 has a non-harmful processing additive.

FIELDS OF APPLICATION

- Masonry Cement

For additional information on **CEMENTIUM 5350 AE** and its use in developing special performance characteristics, contact your local BASF Sales field representative.

FEATURES AND BENEFITS

CEMENTIUM 5350 AE is specially developed with the most active surfactants and effective bonding agent that increase the formation of bubbles in the cement mortar and provide excellent surfaces bonding between the cement mortar and the dry/damp concrete. These double actions improve the Masonry cement workability and placeability significantly.

CEMENTIUM 5350 AE contributes the following benefits to cement manufacturers

- Increased cement fineness with the addition of **CEMENTIUM 5350 AE**.
- Increased entrained air in Masonry cements.
- Improved workability of cement paste.
- Improved the plastering characteristics of cement paste.
- Improved cohesion, reduced segregation and bleeding of cement paste.
- Provided closed textured surface, dense and uniform cement paste.

TYPICAL PERFORMANCE DATA

CEMENTIUM 5350 AE typical performance is as per the following:

Parameter	Range
1. Dosage	500 – 1200 gram/ton
2. Air Content	15% - 25%
3. Flowability	Min 103%

APPLICATION

Dispensing

CEMENTIUM 5350 AE can be added at the clinker feed conveyer belt or directly into the cement mill's first compartment. A proper dosing pump is required to ensure the correct dosage into the cement for obtaining the optimum performance. Our technical supports are available to provide assistance in the use of **CEMENTIUM 5350 AE** with the manual, automatic or computerized dispensing system.

DOSAGE

The typical dosage rate for **CEMENTIUM 5350 AE** is as per the table below:

Type of Cement	Dosage Rate (gram / ton cement)
Masonry Cement	500 – 1200

The air entrainment and workability of Masonry cement is influenced by the chemical and physical composition of the basic ingredients of the cement, grinding process parameters and clinker characteristics. Plant trial or laboratory scale ball mill test is recommended to determine the optimum dosage required to achieve specific requirements.

PACKAGING

CEMENTIUM 5350 AE is supplied in 210L sealed drums, 1000L IBC tanks and bulk delivery.

SHELF LIFE

CEMENTIUM 5350 AE can be stored for 12 months if stored at temperatures above 5°C, in tightly sealed original packaging. If found to be frozen, thaw it at 20°C and reconstitute by stirring.

PRECAUTIONS

BASF Construction Chemicals offices in ASEAN

Singapore
Tel :+65-6861-6766
Fax :+65-6861-3186

Malaysia
Tel :+60-3-5628-3888
Fax :+60-3-5628-3776

Indonesia
Tel :+62-21-526-2481
Fax :+62-21-526-2541

Thailand
Tel :+66-2204-9427
Fax :+66-2664-9267

Vietnam
Tel :+84-650-3743-100
Fax :+84-650-3743-200

Philippines
Tel :+63-2-889-4321
Fax :+63-2-889-4361



The Chemical Company

CEMENTIUM™ 5350 AE (Formerly known as Cementium 250AE)

CEMENTIUM 5350 AE is not a fire or health hazard. Spillages should be washed down immediately with cold water.

For detailed health, safety and environmental recommendations, please consult and follow all instructions in the product Material Safety Data Sheet.

ANsg/C5350AE/v1/020409

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF Construction Chemicals** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.
