

UCRETE® WR POLYKIT

Heavy Duty Polyurethane Concrete Mortar for Coving and Vertical Surfaces

DESCRIPTION

UCRETE WR Polykit is a single layer, seamless, solvent-free, polyurethane system for vertical surfaces with a textured matt finish. It withstands abrasive wear and a wide spectrum of chemicals.

UCRETE WR Polykit is a four component trowel applied coving mortar applied in layers of 3 to 6 mm.

UCRETE WR Polykit should always be applied on primed, UCRETE Primer GC, a solvent free, two components tack primer.

It is fully complementary to all UCRETE Flooring systems.

FIELDS OF APPLICATION

Conditions requiring the maximum of chemical resistance, health and safety and protection of surfaces subject to impact and hot /cold liquid drainage.

Specific applications include:

- coving
- plinths and machine/plant bases
- sump and drain linings
- bunds and bund linings

In all applications where UCRETE Flooring Systems are used.

FEATURES AND BENEFITS

"**HACCP Accredited** Ucrete products have been accredited for use in facilities covered by HACCP accreditation."

Ucrete WR Polykit has approval for use as flooring for HACCP accredited facilities.



Expert application

Installed only by trained and approved specialist contractors.

Fast application/rapid access

Can be applied to 6 day-old-concrete / 2 day-old-polymer screed.

Short curing time and 8 hour access to foot traffic; 20 hours for vehicles.

Hygienic/safe

Slip resistant; non-tainting, non-dusting, monolithic (minimum joints), easy to maintain, microbiologically inert.

Durable/long life

Wide chemical resistance, wear and impact resistant, resists temperatures up to 120°C; 25 years of international use.

Prepacked

Preweighed / prepacked for immediate use; batch-to-batch colour matched for consistency.

TYPICAL PERFORMANCE DATA

(Test data - 28 days @ 20°C)

Density (BS6319:Part 5) : 1,810 kg/m³

Compressive Strength (BS6319:Part 2) : 36 N/mm²

Tensile Strength (ISO R527) : 4.3 M/mm²

Modulus in compression (BS 6319:Part 6) : 2,750

Flexural Strength (ISO178) : 9.2 N/mm²

Concrete Adhesion (BS6319:Part 4) : concrete fails

Coeff. Thermal Expansion (ASTM C531) : 2.4x10⁻⁵ °C⁻¹

Water absorption (CP:BM 2/67/2) : 0 ml

PROPERTIES

Colours : Yellow

: Cream

: Orange

: Red

: Green

: Grey

Thickness : 3 mm to 9 mm

At 3mm, a maximum service temperature of 60°C should be observed. This rises to 120°C at a thickness provide excellent chemical resistance, as in all corrosive situations a full analysis of operation and exposure conditions is required, followed by reference to chemical resistance data to ensure product suitability.

APPLICATION

Surface Preparation

Concrete shall be clean, structurally sound and free from foreign materials, contaminants, oily products and other debris. Concrete surfaces shall be 'visibly dry' with no standing water. The minimum tensile (pull-off) strength shall be 1.5N/mm² and concrete shall have cured for at

BASF Construction Chemicals offices in ASEAN

Singapore

Tel : +65-6861-6766
Fax : +65-6861-3186

Malaysia

Tel : +60-3-3344-3388
Fax : +60-3-3344-2288

Indonesia

Tel : +62-21-893-4339
Fax : +62-21-893-4342

Thailand

Tel : +66-3845-3020
Fax : +66-3845-3029

Vietnam

Tel : +84-650-743-100
Fax : +84-650-743-200

Philippines

Tel : +63-2-632-9995
Fax : +63-2-632-9996

UCRETE[®] WR POLYKIT

least 5 days. Concrete substrates shall incorporate a continuous waterproofing membrane.

Concrete design shall allow provisions for movement joints, as required. In addition, provision shall be made for induced joints to allow any shrinkage of the concrete to occur along defined planes.

All laitance shall be removed. All imperfections such as holes and cracks shall be repaired and leveled with the mean level of the surface. For repairing surface unevenness, EMACO Concrete Repair Systems shall be used.

The whole surface shall be enclosed or impact shot blasted, surface planed, ground or high-pressure water jetted. All high spots shall be removed.

Priming

The initial layer of **UCRETE WR Polykit** shall be applied to a tacky coat of **UCRETE GC Primer**. Subsequent layers are applied direct to re-primer surface.

Areas of UCRETE Primer GC left uncoated for more than 48 hours should be mechanically prepared for being primed again. Do not use UCRETE Primer GC on substrate below 8°C.

Placing

UCRETE WR Polykit shall be mixed and applied only by specialist flooring contractors who have been trained in the correct application procedures.

Sealing

Appearance is enhanced by brushing the uncured surfaces with a solvent-dampened brush or coating with a clear or pigmented polyurethane sealer.

CURING

At 30°C, foot traffic access in 8 hours; vehicular traffic in 16 hours. At 20°C, foot traffic access in 12 hours; vehicular traffic in 24 hours. Full traffic and chemical resistance in 28 days.

CLEANING

Regular cleaning, dry or wet mechanical scrubbing, or hot flushing with detergents or detergent/sterilant products will enhance the floor's appearance and reduce soiling tendencies. Direct steam cleaning is suitable for surfaces applied at more than 8-mm thickness.

ESTIMATING DATA

Coverage is influenced by substrate roughness, porosity and temperature, but allowing for normal wastage factors will be approximately

UCRETE WR – 1.8 to 2.0 kg/m²/mm thickness

UCRETE GC – 0.25 to 0.33 kg/m²

PACKAGING

UCRETE WR, **UCRETE GC Primer** and **UCRETE TC Primer** are supplied in units for immediate use, consisting of:

UCRETE WR Polykit Part 1:	1.06 kg
UCRETE WR Polykit Part 2:	1.06 kg
UCRETE WR Polykit Part 3:	11.35 kg
UCRETE WR Polykit Part 4:	0.4kg

UCRETE GC Primer Part 1:	1.72 kg
--------------------------	---------

UCRETE GC Primer Part 2:	0.88 kg
--------------------------	---------

SHELF LIFE

UCRETE WR Polykit can be kept for 12 months from date of manufacture, in original unopened packaging, if stored under cover and above ground level at 30°C or less, avoiding exposure to direct sunlight.

UCRETE WR Polykit Part 1 must not be allowed to freeze.

PRECAUTIONS

Material Safety Data (MSDS) for each component of **UCRETE WR** are available. Gloves and eye protection shall be worn during mixing and application.

For detailed Health, Safety and Environmental recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.

3-1-2-0808

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF Construction Chemicals** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.